TECHNICAL DATA SHEET



Name Code

LUCRA 01 FO

3109 O1 FO SR

EN ISO Weight **Product Range** Standard Size range Mondopoint **Packaging** 01 F0 SR 300 grams 35 <> 50 10 pairs/carton 20347:2022 (1 shoe in size 42) (same size)



TECHNICAL SPECIFICATIONS















SOLE

SOLE FEATURES



The PU COMB® sole, entirely crafted from polyurethane foam, offers lightness, elasticity, and comfort. Its honeycomb tread provides suction cup grip, superior slip-resistance, and self-cleaning features.









PROTECTIVE ELEMENTS

UPPER

LINING

FOOTBED



water-repellent and stain-resistant



fabric, this lining offers excellent breathability and moisture wicking. It features SANITIZED® tre-

SANITIZED



high breathability, tear, rip, scratch, and friction resistance, plus atment to suppress microorganism growth and prevent odours. Antistatic and anti-odour removable insole with SANITIZED® technology ensuring hygiene and a fresh feeling all day.















SAFETY TECHNICAL SPECIFICATIONS

Description	Measurement Unit	Requirement	Test Result
TOE CAP: Impact resistance	mm	≥ 14	-
TOE CAP: Compression resistance	mm	≥ 14	-
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	-
FOOTWEAR: Antistatic properties (in wet condition)	МΩ	≥ 0,1	5,6
FOOTWEAR: Antistatic properties (in dry condition)	ΜΩ	≤ 1.000	57
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	1,5
UPPER: Water vapour coefficient	mg/cm2	≥ 15	15,1
UPPER: Water penetration after 60 min	g	≤ 0,2	-
UPPER: Water absorption after 60 min	%	≤ 30	-
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	130,7
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	1045,8
OUTSOLE: Abrasion resistance	mm3	≤ 150	90
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	31
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	6,9
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	0

ADDITIONAL FEATURES

Measurement Unit	Requirement	Results	
mA	≤ 1,00	-	
-	autsoles shall not melt and develop any cracks when bent	-	
°C	≤ 10	-	
°C	≤ 22	-	
cm2	after 80 min.	-	
MΩ	≤ 100	-	
	mA - °C °C cm2	mA ≤ 1,00 - autsoles shall not melt and develop any cracks when bent °C ≤ 10 °C ≤ 22 cm2 after 80 min.	

SOLE DESIGN AND PERFORMANCE



ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT **75%**

INDUSTRIES





STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

