# **TECHNICAL DATA SHEET**



Name Code

#### 3406 O2 FO SRC SIATA 02 FO

**EN ISO Product Range** Standard Weight Size range Mondopoint **Packaging** 02 FO SRC 320 grams 35 <> 50 10 pairs/carton 20347:2012 (1 shoe in size 42) (same size)



**TECHNICAL SPECIFICATIONS** 



















**SOLE** 

#### **SOLE FEATURES**











honeycomb tread provides suction cup grip, superior slip-resistance, and self-cleaning features.

**PROTECTIVE ELEMENTS** 

The PU COMB® sole, entirely crafted from polyurethane foam, offers lightness, elasticity, and comfort. Its

#### **UPPER**



#### **FOOTBED**



Hypoallergenic microfiber with high breathability, tear, rip, scratch, and friction resistance, plus

water-repellent and stain-resistant





fabric, this lining offers excellent breathability and moisture wicking. It features SANITIZED® treatment to suppress microorganism growth and prevent odours.



Antistatic and anti-odour removable insole with SANITIZED® technology ensuring hygiene and a fresh feeling all day.















## **SAFETY TECHNICAL SPECIFICATIONS**

Description	Measurement Unit	Requirement	Test Result
TOE CAP: Impact resistance	mm	≥ 14	-
TOE CAP: Compression resistance	mm	≥ 14	-
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	-
FOOTWEAR: Antistatic properties (in wet condition)	МΩ	≥ 0,1	27,2
FOOTWEAR: Antistatic properties (in dry condition)	МΩ	≤ 1.000	368
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	0,9
UPPER: Water vapour coefficient	mg/cm2	≥ 15	15,1
UPPER: Water penetration after 60 min	g	≤ 0,2	0
UPPER: Water absorption after 60 min	%	≤ 30	2,6
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	130.7
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	1045.8
OUTSOLE: Abrasion resistance	mm3	≤ 150	90
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	29
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	4
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	0

## **ADDITIONAL FEATURES**

7.551116117121 271161126			
Measurement Unit	Requirement	Results	
mA	≤ 1,00	-	
-	autsoles shall not melt and develop any cracks when bent	-	
°C	≤ 10	-	
°C	≤ 22	-	
cm2	after 80 min.	-	
MΩ	≤ 100	-	
	mA - °C °C cm2	mA ≤ 1,00  - autsoles shall not melt and develop any cracks when bent  °C ≤ 10  °C ≤ 22  cm2 after 80 min.	

## **SOLE DESIGN AND PERFORMANCE**



TRACTION STABILITY GRIP BRAKING SELF-CLEANING LADDER GRIP

ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT **75%** 

## **INDUSTRIES**



## STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

