# **TECHNICAL DATA SHEET**



Name Code

#### **MATERA S1** 36111N S1 FO SR

Standard

**EN ISO Product Range** Weight Size range Mondopoint **Packaging** 435 grams 10 pairs/carton S1 F0 SR 20345:2022 35 <> 48



#### **TECHNICAL SPECIFICATIONS**









(1 shoe in size 42)







(same size)



#### **SOLE**

#### **SOLE FEATURES**

## MICROLIGHT










**FOOTBED** 



#### **PROTECTIVE ELEMENTS**





**UPPER** 

and treated for a velvety touch, combines softness with resilience for daily work.



**LINING** 

featuring a microchannel network for unparalleled breathability and antimicrobial properties to prevent odors and microorganism growth.



SANITIZED®

removable insole with SANITIZED® technology ensuring hygiene and a fresh feeling all day.

## **EXTRA**

Requirement



Safety toe cap made from composite

material, shielding toes from impacts up to 200 Joules and compressions

up to 15 kN. It is non-magnetic,

non-conductive, and provides superior thermal insulation













**Test Result** 

## SAFETY TECHNICAL SPECIFICATIONS

Description

2000 Page	mododromont ont	rioquii oiliolii	10011100011
TOE CAP: Impact resistance	mm	≥ 14	16,5
TOE CAP: Compression resistance	mm	≥ 14	19,5
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	-
FOOTWEAR: Antistatic properties (in wet condition)	МΩ	≥ 0,1	11,4
FOOTWEAR: Antistatic properties (in dry condition)	МΩ	≤ 1.000	71
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	9,6
UPPER: Water vapour coefficient	mg/cm2	≥ 15	84,9
UPPER: Water penetration after 60 min	g	≤ 0,2	-
UPPER: Water absorption after 60 min	%	≤ 30	-
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	81,1
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	649,1
OUTSOLE: Abrasion resistance	mm3	≤ 150	67
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	29
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	6,9
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	1,2

**Measurement Unit** 

## **ADDITIONAL FEATURES**

Measurement Unit	Requirement	Results		
mA	≤ 1,00	-		
-	autsoles shall not melt and develop any cracks when bent	-		
°C	≤ 10	-		
°C	≤ 22	-		
cm2	after 80 min.	-		
MΩ	≤ 100	-		
	mA - °C °C cm2	mA ≤ 1,00  - autsoles shall not melt and develop any cracks when bent  °C ≤ 10  °C ≤ 22  cm2 after 80 min.		

## **SOLE DESIGN AND PERFORMANCE**



ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT 45%

## **INDUSTRIES**

































## STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

