TECHNICAL DATA SHEET



Name Code

PUNTO 36569N SB A E SRC

Product Range Standard EN ISO Weight Size range Mondopoint Packaging

SB A E SRC 20345:2011 400 grams 35 <> 48 11 10 pairs/carton



TECHNICAL SPECIFICATIONS









(1 shoe in size 42)







(same size)



SOLE

SOLE FEATURES

AUULU CUL

MICROLIGHT

The MICROLIGHT® soles, which combine cutting-edge compounds for both the PU foam midsole and the compact PU outsole, excel in lightness, flexibility, and elasticity, while offering exceptional stability and wear





LINING



PROTECTIVE ELEMENTS



Heat-treated and epoxy-coated safety toe cap withstands impacts up to 200 Joules and compressions up to 15 kN. Stainless steel fibers increase durability and beveled edges enhance comfort.

UPPER

Hypoallergenic microfiber with high breathability, tear, rip, scratch, and friction resistance, plus

Made from durable multi-layer fabric, this lining offers excellent breathability and moisture wicking. It features SANITIZED® treatment to suppress microorganism growth and prevent odours.

SANITIZED



FOOTBED

Antistatic and anti-odour removable insole with SANITIZED® technology ensuring hygiene and a fresh feeling all day.



Requirement





Test Result



water-repellent and stain-resistant





SAFETY TECHNICAL SPECIFICATIONS

Description

Description	Measurement out	nequirement	rest nesuit
TOE CAP: Impact resistance	mm	≥ 14	16,5
TOE CAP: Compression resistance	mm	≥ 14	18
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	-
FOOTWEAR: Antistatic properties (in wet condition)	МΩ	≥ 0,1	42
FOOTWEAR: Antistatic properties (in dry condition)	МΩ	≤ 1.000	185
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	0,9
UPPER: Water vapour coefficient	mg/cm2	≥ 15	15,1
UPPER: Water penetration after 60 min	g	≤ 0,2	-
UPPER: Water absorption after 60 min	%	≤ 30	-
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	130,7
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	1045,8
OUTSOLE: Abrasion resistance	mm3	≤ 150	92
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	28
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	4
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	0

Measurement Unit

ADDITIONAL FEATURES

Measurement Unit	Requirement	Results
MO		
MΩ	≤ 1,00	-
-	autsoles shall not melt and develop any cracks when bent	-
°C	≤ 10	-
°C	≤ 22	-
cm2	after 80 min.	-
ΜΩ	≤ 100	-
	cm2	cm2 after 80 min.

SOLE DESIGN AND PERFORMANCE



THACTION STABILITY GRIP BRAKING SELF-CLEANING LADDER GRI

ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

0 MINMUM VALUE 20 TEST RESULT 29 45%

INDUSTRIES



STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat.
 Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

