TECHNICAL DATA SHEET



Name Code

NAPOLI S1 36611N S1 FO SR

Standard

EN ISO Weight **Product Range** Size range Mondopoint **Packaging** 445 grams 35 <> 48 10 pairs/carton S1 F0 SR 20345:2022



TECHNICAL SPECIFICATIONS









(1 shoe in size 42)







(same size)



SOLE

SOLE FEATURES

MICROLIGHT








LINING



FOOTBED



Safety toe cap made from composite

material, shielding toes from impacts up to 200 Joules and compressions

up to 15 kN. It is non-magnetic,

PROTECTIVE ELEMENTS





UPPER

and treated for a velvety touch, combines softness with resilience antimicrobial properties to prevent for daily work.



odors and microorganism growth.

AIRNET

Antistatic and anti-odour removable insole with SANITIZED® technology ensuring hygiene and a fresh feeling all day.

SANITIZED®



Requirement



Test Result











SAFETY TECHNICAL SPECIFICATIONS

Description

Description	weasurement out	nequirement	rest nesult
TOE CAP: Impact resistance	mm	≥ 14	16,5
TOE CAP: Compression resistance	mm	≥ 14	18,5
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	-
FOOTWEAR: Antistatic properties (in wet condition)	МΩ	≥ 0,1	11,5
FOOTWEAR: Antistatic properties (in dry condition)	МΩ	≤ 1.000	121
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	9,6
UPPER: Water vapour coefficient	mg/cm2	≥ 15	84,9
UPPER: Water penetration after 60 min	g	≤ 0,2	-
UPPER: Water absorption after 60 min	%	≤ 30	-
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	81,1
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	649,1
OUTSOLE: Abrasion resistance	mm3	≤ 150	67
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	28
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	6,9
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	1,2

Measurement Unit

ADDITIONAL FEATURES

7.5511101117.111111111111111111111111111				
Measurement Unit	Requirement	Results		
mA	≤ 1,00	-		
-	autsoles shall not melt and develop any cracks when bent	-		
°C	≤ 10	-		
°C	≤ 22	-		
cm2	after 80 min.	-		
MΩ	≤ 100	-		
	mA - °C °C cm2	mA ≤ 1,00 - autsoles shall not melt and develop any cracks when bent °C ≤ 10 °C ≤ 22 cm2 after 80 min.		

SOLE DESIGN AND PERFORMANCE



ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT 45%

INDUSTRIES































STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

