TECHNICAL DATA SHEET



(same size)

Name Code

HV NAPOLI S1P 36622N S1PS FO SR

EN ISO Standard Weight **Packaging Product Range** Size range Mondopoint S1PS F0 SR 20345:2022 510 grams 35 <> 48 10 pairs/carton





















Measurement Unit



SOLE

SOLE FEATURES

(1 shoe in size 42)













PROTECTIVE ELEMENTS





UPPER



LINING



FOOTBED

Safety toe cap made from composite material, shielding toes from impacts up to 200 Joules and compressions up to 15 kN. It is non-magnetic, non-conductive, and provides superior thermal insulation

layer polyester, 40% lighter than steel, yet equally resistant up to 1,100 Newtons. It is non-magnetic, insulating and hypoallergenic.

and treated for a velvety touch, combines softness with resilience for daily work.

featuring a microchannel network for unparalleled breathability and antimicrobial properties to prevent odors and microorganism growth.

Antistatic and anti-odour removable insole with SANITIZED® technology ensuring hygiene and a fresh feeling all day.



Requirement





Test Result





SAFETY TECHNICAL SPECIFICATIONS

Description

2 de la	moadaroment omt	moquino mont	10011100011
TOE CAP: Impact resistance	mm	≥ 14	16,5
TOE CAP: Compression resistance	mm	≥ 14	18,5
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	pass
FOOTWEAR: Antistatic properties (in wet condition)	ΜΩ	≥ 0,1	11,5
FOOTWEAR: Antistatic properties (in dry condition)	ΜΩ	≤ 1.000	121
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	9,6
UPPER: Water vapour coefficient	mg/cm2	≥ 15	84,9
UPPER: Water penetration after 60 min	g	≤ 0,2	-
UPPER: Water absorption after 60 min	%	≤ 30	-
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	81,1
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	649,1
OUTSOLE: Abrasion resistance	mm3	≤ 150	67
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	28
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	6,9
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	1,2

ADDITIONAL FEATURES

Measurement Unit	Requirement	Results		
mA	≤ 1,00	-		
-	autsoles shall not melt and develop any cracks when bent	-		
°C	≤ 10	-		
°C	≤ 22	-		
cm2	after 80 min.	-		
MΩ	≤ 100	-		
	mA - °C °C cm2	mA ≤ 1,00 - autsoles shall not melt and develop any cracks when bent °C ≤ 10 °C ≤ 22 cm2 after 80 min.		

SOLE DESIGN AND PERFORMANCE



TRACTION STABILITY GRIP BRAKING SELF-CLEANING LADDER GRIP

ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT 45%

INDUSTRIES





























STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

