TECHNICAL DATA SHEET



Name Code

NUOVO STRADA S2 6229N S2 FO SR

EN ISO Standard Weight **Packaging Product Range** Size range Mondopoint S2 F0 SR 20345:2022 520 grams 35 <> 50 10 pairs/carton (1 shoe in size 42) (same size)

STROM >>

TECHNICAL SPECIFICATIONS

















SOLE



















FOOTBED



PROTECTIVE ELEMENTS



UPPER







Heat-treated and epoxy-coated safety toe cap withstands impacts up to 200 Joules and compressions up to 15 kN. Stainless steel fibers increase durability and beveled edges enhance comfort

a polyurethane film application makes this genuine leather completely water-resistant, offering

enhanced protection.

Microfiber lining, treated to inhibit bacterial and microbial growth, boasts exceptional breathability and superior abrasion resistance

Removable insole that distributes weight evenly, adapts to foot morphology and has anti-static, antibacterial, and antifungal properties. A cushioned heel insert adds comfort.









SAFETY TECHNICAL SPECIFICATIONS

TOE CAP: Impact resistance mm TOE CAP: Compression resistance mm	≥ 14 ≥ 14	17
TOE CAP: Compression resistance mm	≥ 14	
		19
ANTI-PUNCTURE PLATE: Penetration resistance N	≥ 1.100	-
FOOTWEAR: Antistatic properties (in wet condition) ΜΩ	≥ 0,1	17,7
FOOTWEAR: Antistatic properties (in dry condition) $M\Omega$	≤ 1.000	47,3
UPPER: Water vapour permeability mg/cm2	2*h ≥ 0,8	1,5
UPPER: Water vapour coefficient mg/cm2	2 ≥ 15	19,2
UPPER: Water penetration after 60 min g	≤ 0,2	0
UPPER: Water absorption after 60 min %	≤ 30	2,2
INTERNAL LINING: Water vapour permeability mg/(cm	n2*h) ≥ 2,0	28,6
INTERNAL LINING: Water vapour coefficient mg/cm2	2 ≥ 20	229,4
OUTSOLE: Abrasion resistance mm3	≤ 150	54
OUTSOLE: Energy absorption of seat region (E)	≥ 20	33
OUTSOLE: Flexural resistance mm	≤ 4	0,5
OUTSOLE: Interlayer bond strength N/mm	≥ 4	5,1
OUTSOLE: Resistance to fuel oil (FO) %	≤ 12	2,7

ADDITIONAL FEATURES

Measurement Unit MA	Requirement ≤ 1,00 autsoles shall not melt and develop any cracks when bent	Results -
mA -	autsoles shall not melt and	-
-		-
°C	≤ 10	-
°C	≤ 22	-
cm2	after 80 min.	-
MΩ	≤ 100	-

SOLE DESIGN AND PERFORMANCE



ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT **75%**

INDUSTRIES



























STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

